



DUPONT™ 5785R

ALUMINUM BONDABLE AU CONDUCTOR

PRODUCT DESCRIPTION

DuPont™ 5785R is a very high density gold conductor composition. Suitable for applications requiring high frequency and/or fine line conductor features.

PRODUCT BENEFITS

- Lead, Phthalate and Cadmium free*
- Excellent for fine line features
- Excellent wire bond acceptance yields with 1&2 mil Au and 1&10 mil Al wire
- Dense fired film
- Smooth surface appearance
- REACH and RoHs compliant
- Compatible with DuPont Pb-free Resistor Series and Dielectric QM44

*Lead, Phthalate and Cadmium “free” as used herein means that lead, phthalate and cadmium are not intentional ingredients in and are not intentionally added to the referenced product. Trace amounts however may be present.

PROCESSING

Substrates

Properties are based on tests using 96% alumina substrates. Substrates of other compositions and from various manufacturers may result in variations in performance properties.

Screen Printing Recommendation

A 325 or 400-mesh stainless steel screen with a 12.5µm (0.5mil) emulsion thickness is recommended. Printing speeds up to 15 cm/s (6 in/s) can be used.

Drying

Allow the wet print to level for 10-15 minutes at room temperature. Dry for 15 minutes at 150°C.

Firing

Dried prints should be fired in a belt furnace. Use a 30 or 60-minute cycle with a peak temperature of 850°C. No significant changes are observed after refires at 850°C.

Table 1 - Typical Fired Properties

Test	Results
Line Resolution (lines/spaces)	150/100 µm [6/4mil]
Fired Thickness	5 - 9 µm
Resistivity	< /=6.0mohm/[] 10µm fired
Gold Wire Bonding ¹	1 mil Au wire >8g 2 mil Au wire >35g 1 mil no misses in 1600 trials 1 mil Au on QM44 wire >8g
Aluminum Wire Bonding ^{1,2}	1 mil Al wire initial >8 g 1 mil Al wire aged 315C/1.25hr >5 g 10 mil Al wire initial >500 g 10 mil Al wire aged 315C/1.25hr >350 g

¹On Alumina

²Passes 1,000hr/150°C Aging

Table 2 - Composition Properties

Test	Results
Viscosity (Pa.s) (Brookfield HBT, SC04 14/6R [UC&SP], 10 RPM, 25°C)	300 - 450
Solids (750°C) [%]	87 - 89
Coverage, cm ² /g	60 - 90
Thinner	DuPont™ 8250

Tables 1 and 2 show anticipated typical physical properties for DuPont™ 5785R based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.

STORAGE AND SHELF LIFE

Containers should be stored, tightly sealed, in a clean, stable environment at room temperature (<25°C). Shelf life of material in unopened containers is six months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use.

SAFETY AND HANDLING

For Safety and Handling information pertaining to this product, read the Material Safety Data Sheet (MSDS).



DUPONT™ 5785R ALUMINUM BONDABLE AU CONDUCTOR

**FOR MORE INFORMATION ON DUPONT™ 5785R OR OTHER DUPONT MICROCIRCUIT MATERIALS, PLEASE CONTACT
YOUR LOCAL REPRESENTATIVE:**

Americas

DuPont Microcircuit Materials
14 TW Alexander Drive
Research Triangle Park, NC 27709
USA
Tel +1 800 284 3382 (calls within USA)
Tel +1 919 248 5188 (calls outside USA)

Europe, Middle East & Africa

Du Pont (UK) Ltd
Coldharbour Lane
Bristol BS16 1QD
UK
Tel +44 117 931 3191

Asia

Du Pont Kubushiki Kaisha
MCM Technical Lab
DuPont Electronics Center
KSP R&D B213, 2-1,
Sakado 3-chome, Takatsu-ku,
Kawasaki-shi, Kanagawa, 213-0012
Japan
Tel +81 44 820 7575

DuPont Taiwan Ltd
45, Hsing-Pont Road
Taoyuan, 330
Taiwan
Tel +886 3 377 3616

DuPont China Holding Company Ltd
Bldg. 11, 399 Keyuan Road
Zhangjiang Hi-Tech Park
Pudong New District
Shanghai 201203
Tel +86 21 3862 2888

DuPont Korea Inc.
3-5th Floor, Asia tower #726
Yeoksam-dong, Gangnam-gu
Seoul 135-719, Korea
Tel +82 2 2222 5275

E.I. DuPont India Private Limited
7th Floor, Tower C, DLF Cyber Greens
Sector-25A, DLF City, Phase-III
Gurgaon 122 002 Haryana, India
Tel +91 124 409 1818

Du Pont Company (Singapore) Pte Ltd
1 HarbourFront Place, #11-01
HarbourFront Tower One
Singapore 098633
Tel +65 6586 3022

mcm.dupont.com

Copyright © 2015 DuPont. All rights reserved. The DuPont Oval Logo, DuPont™, and all DuPont products denoted with ® or ™ are registered trademarks or trademarks of E. I. du Pont de Nemours and Company or its affiliates.

This information corresponds to our current knowledge on the subject. It is offered solely to provide possible suggestions for your own experiments. It is not intended, however, to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in end-use conditions, DuPont makes no warranties, and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right.

CAUTION: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Medical Caution Statement," H-50102-5 K-28890 (6/15)